

PREMIUM COLORS

Width: 60"




R-099 White




R-117 Raw



R-126 Linen



R-100 Beige




R-178 Toast




R-143 Hemp Beige



R-139 Heather Beige



R-775 Linen Tweed



R-554 Yellow



R-567 Orange



R-185 Pumpkin



R-176 Red




R-773 Red Tweed



R-182 Vermillion




R-177 Burgundy



R-104 Chestnut




R-156 Brown




R-169 Steel Blue **NEW**



R-911 Baltic **NEW**



R-769 Baltic Tweed **NEW**



R-170 Admiral Blue



R-172 Blue




R-173 Dark Blue **NEW**



R-174 Navy Blue



R-772 Blue Tweed



R-175 Captain Navy



R-171 Turquoise **NEW**



R-160 Pistachio **NEW**




R-142 Emerald




R-771 Green Tweed



R-292 Teal **NEW**



R-163 Green




R-102 Forest Green




R-114 Pearl **NEW**



R-196 Titanium **NEW**



R-123 Argenta Grey



R-138 Cadet Grey




R-161 Grey



R-127 Moonrock




R-194 Ash **NEW**



R-198 Nickel



R-164 Charcoal Grey



R-770 Charcoal Tweed



R-103 Black



Awning and Marine
Acrylic Fabric
60" Collection

Technical Specifications

FABRIC TYPE		
Name of Fabric	Recacril®	
Base Fabric	100% Solution dyed acrylic fibers	
CHARACTERISTICS		
Weight	9 oz. +/- 5%	
Standard Put Up	65.64 yards / 60 meters	
Finish	Fluorocarbon / Resin	
Finished Width	60" / 152 cm	
Styles	44 solids	
Limited Warranty	10 years	
SPECIFICATIONS		
UV Resistance	1500 + hours	TEST METHOD AATCC-16
Abrasion Rating	40,000 Rubs	ASTM-4157
Hydrostatic	40 cm	AATCC-127 Method B
Puncture Strength	38 lbs	ASTM-751
WARP / WEFT		
Tear Strength	11.5 lbs / 7.7 lbs	ASTM D-2261
Tensile Strength	287 lbs / 149 lbs	ASTM D-5034 Grab
Shrinkage	0.10% / 0%	Method 5804
Stretch	0% / 0%	ASTM D-2594

SAFETY, HEALTH AND ENVIRONMENT



ADVANTAGES AND BENEFITS



Care and Cleaning

Proper care and cleaning should be taken to ensure the life of Recacril® outdoor fabrics.

For regular care and maintenance, the excess dirt should be brushed from the fabric using a soft brush; the fabric should then be sprayed with warm water (not exceeding 100° F) and air-dried.

Periodically, the fabric should undergo a more thorough cleaning. Again, brush fabric with a soft bristled brush, spray with warm water, then apply a gentle soap. Let stand for 10 to 20 minutes taking care not to let it dry, then rinse thoroughly and air-dry. Do not use detergents and/or solvents.

When possible, please make sure to leave retractable awnings deployed or extended until the fabric cover is dried completely. This will help prevent mildew from forming.

Infinity Process

The Recacril® and Recsystem® canvases are treated with a special technological process to ensure the lasting quality of the fabric. In this process, nanoparticles completely cover the surface of the fibers in the fabric, forming a permanent coat. After treatment, both the surface and the inside of the fabric are permanently protected against dirt build-up, and adverse effects of a wide variety of atmospheric agents.

The low reactivity and high stability of the Infinity treatment endows long-term protection to the awning, especially against mildew, and provides excellent water and oil repellence.



The technical characteristics shown are average values with a +/-5% tolerance. The data indicated in this document are the result of laboratory tests or technical calculations in accordance with current regulations. As our products are constantly evolving, according to market demands and technical progress, S.A. RECASENS reserves the right to change these data at any time. It is the customer's responsibility to check that the data that they are consulting are from the most recent update. The customer shall be responsible for the correct use of the fabric with regard to the applications for which it has been designed and recommended. S.A. RECASENS accepts no responsibility regarding the assembly and installation of its products. It also accepts no responsibility for its products being installed in non-compliance with current regulations. The photographs and descriptions in this catalogue have no contractual value, they are indicated for guidance only. S.A. RECASENS reserves the right to make any modifications it deems appropriate. Copyright©2021 S.A. RECASENS. All rights reserved.